

1. Manufacturer

KING ARTHUR INDUSTRIES CO., LTD.

No.512, Chioufen Rd, Luntze Tsun, Yung-Ching Hsaing, ChangHua Hsien, Taiwan

TEL: +886-4-8223131 FAX: +886-4-8229956, E-mail: info@osst-surfaces.com

2. Product name:

TeamPlay- Marble

2.1 Product description

2.1.a Prefabricated sport surface vulcanized in two layers construction consists of EPDM, naturel rubber, mineral fillers, stabilizing agents, color pigments, none permeable, textured wear resistant surface layer and shock absorbing layer bonded by vulcanization.

2.1.b Color : 10 standard colors (see catalogue)

2.1.c Thickness: 6mm, 8mm,10mm

2.1.d Finish : smooth surface with marble color.

2.1.e Dimensions: in Roll : Width. 100cm to 125cm (3' 4" to 4'1.2")

Length 6M to 15M (19'8" to 49'2.6")

2.2 Product properties

| Test items | Test Methods | Requirements | Thickness | | |
|---|--------------|--------------|-----------|-----------|-----------|
| | | | 6mm | 8mm | 10mm |
| Force reduction | ASTM F2772 | >10% | 10%±3 | 12%±3 | 15%±3 |
| Vertical deformation | ASTM F2772 | <3.5mm | 0.4mm±0.2 | 0.5mm±0.2 | 0.6mm±0.2 |
| Slip/Skid Resistance (Dry) | ASTM F2772 | 80~110 | >90 | >90 | >90 |
| Ball Rebound | ASTM F2772 | >90% | >96% | >96% | >96% |
| Elongation at break | ASTM D412 | ≥70% | ≥300% | ≥300% | ≥300% |
| Tensile Strength | ASTM D412 | ≥75psi | ≥300 psi | ≥300 psi | ≥300 psi |
| Hardness of full layer | ASTM D2240 | ** | 62±3 | 62±3 | 62±3 |
| Abrasion resistance (H18,1000g,1000cycles) | ASTM D3389 | ≤1g | ≤0.5g | ≤0.5g | ≤0.5g |
| Fungi resistance | ASTM G21-15 | Under Level1 | Level 0 | Level 0 | Level 0 |
| Resistance of Chemicals | ASTM F925 | No change | Compliant | Compliant | Compliant |
| Color Heat stability | ASTM F1514 | ≤8.0ΔE | 0.61 | 0.61 | 0.61 |
| Color Light stability | ASTM F1515 | ≤8.0ΔE | 1.86 | 1.86 | 1.86 |
| Critical Radiant Flux | ASTM E648 | ≥0.1w/cm2 | Compliant | Compliant | Compliant |
| Resistance to impact | EN1517 | no cracking | No damage | No damage | No damage |
| Resistance to indentation | EN1516 | ≤0.5 mm | <0.4mm | <0.4mm | <0.4mm |
| Resistance to a rolling load | EN1569 | ≤0.5 mm | <0.3mm | <0.3mm | <0.3mm |
| GREENGUARD Certification | GREENGUARD | Compliant | Compliant | Compliant | Compliant |
| GREENGUARD Gold | GREENGUARD | Compliant | Compliant | Compliant | Compliant |
| REACH SVHC items | REACH | Compliant | Compliant | Compliant | Compliant |

Results obtained from manufacturing controls can vary between production lots and don't constitute representations or warranties as to any particular product lot. KING ARTHUR COMPANY keeps the right to modify the characteristics of the products anytime.

3 · Adhesive

Adhesive: Two component polyurethane glue.

***Please contact the glue manufacturer for product recommendation based on project location.**

4. Delivery and Storage

- 4.1 The general contractor shall provide a secure, clean and dry storage location, which is protected from exposure to harmful weather conditions at 65 to 104 degrees F (18 to 40 degrees °C).
- 4.2 Store sports flooring rolls in original wrappings, and label intact until time of installation.
- 4.3 Keep the rolls are well positioned in an upright position with pallet, and don't stack anything on top includes stack rolls on top of each other.

5. References

5.1 Association(s)

ASTM International (ASTM)

5.2 ASTM International (ASTM)

ASTM D412: Standard Test Methods for Vulcanized Rubber and Thermoplastic Elastomers—Tension.
ASTM D2240: Standard Test Method for Rubber Property (Durometer Hardness).
ASTM D3389: Standard Test Method for Coated Fabrics Abrasion Resistance (Rotary Platform Abrader).
ASTM F925: Standard Test Method for Resistance to Chemicals of Resilient Flooring.
ASTM F2772: Standard Specification for Athletic Performance Properties of Indoor Sports Floor Systems.
ASTM F2157: Standard Specification for Synthetic Surfaced Running Tracks
ASTM F2117: Standard Test Method for Vertical Rebound Characteristics of Sports Surface
ASTM E303: Standard Test Method for Measuring Surface Frictional Properties
ASTM F2569: Standard Test Method for Evaluating the Force Reduction Properties of Surfaces for Athletic
ASTM E648: Standard Test Method for Critical Radiant Flux of Floor Covering Systems Using a Radiant
ASTM F1514: Standard Test method for Measuring Heat Stability of Resilient Flooring by Color Change.
ASTM F1515: Standard Test Method for Measuring Light Stability of Resilient Flooring by Color Change.

5.3 European Committee for Standardization (EN)

EN 13036-4: Road and airfield surface characteristics. Test methods -the pendulum test for friction.
EN 14808: Surfaces for sports areas. Determination of shock absorption.
EN 14809: Surfaces for sports areas. Determination of vertical deformation.
EN 12235: Surfaces for sports areas - Determination of vertical ball behavior
EN 1517: Surfaces for sports areas. Determination of Resistance to impact.
EN 1516: Surfaces for sports areas. Determination of Resistance to indentation.
EN 1569: Surfaces for sports areas. Determination of Resistance to a rolling load.

5.4 GREENGUARD Environmental Institute (GEI)

GREENGUARD Certification: Compliant with stringent emission levels for over 360 VOCs, plus a limit on the total of all chemical emissions combined (TVOC).
GREENGUARD Gold Certification: Compliant with safety factors to account for sensitive individuals (such as children and the elderly) and ensure that a product is acceptable for use in environments such as schools and healthcare facilities.

5.5 REACH:

Regulation (EC) No 1907/2006 of the European Parliament and of the Council of 18 December 2006 concerning the Registration, Evaluation, Authorization and Restriction of Chemicals (REACH), establishing European Chemicals Agency.

5.6 SVHC:

Candidate List of substances of very high concern for Authorization (published in accordance with Article 59(10) of the REACH Regulation)